

SLAGGING AGENTS
MATERIAL : PERLITE



Typical Chemical Composition (on dry basis)	
	% wgt
SiO ₂	72.0±2.0
Al ₂ O ₃	12.5±1.0
Fe ₂ O ₃	1.4±0.3
MgO	0.2±0.1
CaO	0.7±0.2
Na ₂ O	3.8±0.6
K ₂ O	5.6±0.6
Loss Of Ignition (due to combined water)	3.2±0.6