

**AGENTS DE DECRASSAGE**  
**PERLITE**



**Typical Chemical Composition**  
( on dry basis )

	% wgt
SiO <sub>2</sub>	72.0±2.0
Al <sub>2</sub> O <sub>3</sub>	12.5±1.0
Fe <sub>2</sub> O <sub>3</sub>	1.4±0.3
MgO	0.2±0.1
CaO	0.7±0.2
Na <sub>2</sub> O	3.8±0.6
K <sub>2</sub> O	5.6±0.6
Loss Of Ignition (due to combined water)	3.2±0.6